



TECHNICAL SHEET

Product

Dimensions: 0.16mm x 48mm x 10m (ou 30m)

Testing method: ULC S-102

- 1 - Resin of PVC
- 2 - DOP laminator
- 3 - Lead sulfate stabilizer
- 4 - Stearic acid
- 5 - Natural rubber
- 6 - Sticky agent

ULC S-102 CLASSIFICATION

Flame spread: < 25
Smoke spread: < 50

Characteristics	ULC S-102 Requirements	Typical value
Thickness (mm):	Min. 0.15	0.17
Resistance to tension (mpa):	Min. 13.8	15
Extension	Min. 100%	180%
Force	Min. 39.37	50
Adhesion (n / 10mm)	Min. 1.75	2.5
Adhesion support (n / 10mm)	Min. 1.75	1.9
Corrosion	1 x 106	Pass
Deformation	Max. 65%	Pass
Retention of the force of adhesion to the storage		Pass
Humidity absorbtion - Maintains 90% of its original force to the absorbtion of humidity		Pass
Exposure to heat - No cracking, rippling and effect on the corrosion		Pass

Guarantee

Trans Continental Equipment guarantees that the SimpleTape® product will be free from defects in materials and workmanship for a period of one (1) year from date of purchase only. Conditional on our instructions for installation, use, operation and cleaning. Materials and technical specifications may be changed without notice.

PROJECT	# PROJECT
ARCHITECT	ENGINEER
SUBMITTED BY	DATE